

JC20 Rec'd PCT/PTO 13 MAY 2005

Docket No.: 1592-0155PUS1
(PATENT)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:
Masashi NAKAMURA et al.

Application No.: Not Yet Assigned

Confirmation No.: N/A

Filed: May 13, 2005

Art Unit: N/A

For: EPITAXIAL GROWTH METHOD AND
SUBSTRATE FOR EPITAXIAL GROWTH

Examiner: Not Yet Assigned

LETTERCommissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:

The PTO is requested to use the amended sheets/claims attached hereto (which correspond to Article 19 amendments or to claims attached to the International Preliminary Examination Report (Article 34)) during prosecution of the above-identified national phase PCT application.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37.C.F.R. §1.16 or 1.14; particularly, extension of time fees.

10/534695

JC20 Rec'd PTO 13 MAY 2005

Application No.: Not Yet Assigned

Docket No.: 1592-0155PUS1

Dated: May 13, 2005
MSW/nl

Respectfully submitted,

By  (JD 004006)

Marc S. Weiner

Registration No.: 32,181

BIRCH, STEWART, KOLASCH & BIRCH, LLP

8110 Gatehouse Rd

Suite 100 East

P.O. Box 747

Falls Church, Virginia 22040-0747

(703) 205-8000

Attorney for Applicant

Attachment(s)

13
RECEIVED
ART 31 AMDT

10/534695
13 MAY 2005

CLAIMS

1. An epitaxial growth method comprising: supporting a substrate for growth with a substrate supporter, forming a compound semiconductor layer comprising 3 or 4 elements on the substrate for growth by metal organic chemical vapor deposition, polishing the substrate so that an angle of gradient is 0.00° to 0.03° or 0.04° to 0.24° with respect to (100) direction in an entire effective area of the substrate, and forming the compound semiconductor layer to be $0.5\mu\text{m}$ thick or more on the substrate by using the substrate for growth.

2. The epitaxial growth method as claimed in claim 1, further comprising: forming a buffer layer on the substrate for growth, and forming the compound semiconductor layer on the buffer layer.

3. The epitaxial growth method as claimed in claim 1 or 2, wherein the compound semiconductor layer is a III-V group compound semiconductor layer containing at least As.

4. The epitaxial growth method as claimed in claim 3, wherein the compound semiconductor layer is an InGaAs layer or an InAlAs layer.

5. The epitaxial growth method as claimed in claim 3 or 4, wherein the substrate for growth is a semiconductor crystal substrate having dislocation density of 5000cm^{-2} or less.

6. The epitaxial growth method as claimed in claim 5, wherein the substrate for growth is an InP substrate.

7. A substrate for epitaxial growth used for an epitaxial growth method in which a compound semiconductor layer comprising 3 or 4 elements is formed on the substrate for growth by metal organic chemical vapor deposition, wherein an angle of gradient is 0.00° to 0.03° or 0.04° to 0.24° with respect to (100) direction in an entire effective area of the substrate..

8. The substrate for epitaxial growth as claimed in claim 7, wherein the substrate is a semiconductor crystal substrate having dislocation density of 5000cm^{-2} or less.

9. The substrate for epitaxial growth as claimed in claim 7 or 8, wherein the substrate is an InP substrate.